

CLEARPACK – GLTE/M

SKIN PACKAGING FILM FOR NON-COATED CARDBOARDS

The film CLEARPACK -GLTEM can be used with **non-coated** board and is the ideal film for industrial or retail skin packaging.

It is one of the most economical means of safely transporting and presenting delicate products.



TECHNICAL CHARACTERISTICS OF CLEARPACK GLTE/M

Width of film	Suitable for all skin packaging machines on the market.						
Thickness of film (in mils)	3	4	5	6	7	8	10
Length of rolls (feet)	1640	1300	1140	980	810	650	550
Yield (IN ² /Lb)	9900	7470	5980	4950	4270	3740	2990
Diameter of rolls	10 inch (Approx)						
Interior diameter of core	3 inch						
Temperature of forming	226° F (Approx)						
Approximate weight per inch of width:	2 Lbs.						
Values of mechanical resistance. Break strain.	Length	Unit	Value(*)	Norm			
	Width	N/mm ²	27	ASTM-D382			
Elongation at rupture	Length	N/mm ²	21	ASTM-D382			
	Width	%	350-550	ASTM-D382			
Shore D hardness	Length	%	450-750	ASTM-D382			
	Width	%	45	ASTM-D2240-75			
(*) Values for 6 mils foil							
Permeability to water vapour (film thickness of 0,10 mm) DIN 53122	g/m ² 1,4 ÷ 1,5 in 24 hours for a temperature of 73,4° F, 0-85% of relative humidity.						
Resistance to chemicals	At a temperature of 66° F CLEARPACK is resistant to almost all bases and acids.						
Chemically neutral/physiologically out of danger	The film contains neither plasticizer nor stabilizer.						
Environment, ecology	The film can be destroyed by incineration without any emission of poisonous gases. The film acts neutrally, and produces no chemical reaction and in no way affects the quality of underground water sources.						

WHICH CARDBOARD TO USE? Non-coated OR coated

Europack, Inc.
P. O. BOX 1210 - Hockessin, DE 19707
Tel: +(302) 295-6256 Fax: +(302) 295-6259 europack@europackinc.com
www.europackinc.com

EUROPACK
INC
PACKAGING FILMS